

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : H02N 1/00		A1	(11) International Publication Number: WO 00/39914
			(43) International Publication Date: 6 July 2000 (06.07.00)
(21) International Application Number: PCT/US99/28066			(81) Designated States: CA, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(22) International Filing Date: 23 November 1999 (23.11.99)			
(30) Priority Data: 09/223,368 29 December 1998 (29.12.98) US			
(71) Applicant: HONEYWELL INC. [US/US]; Honeywell Plaza, Minneapolis, MN 55408 (US).			
(72) Inventors: CABUZ, Cleopatra; 6429 Tingdale Avenue South, Edina, MN 55439 (US). HORNING, Robert, D.; 14411 Alabama Avenue South, Savage, MN 55378 (US). HERB, William, R.; 1419 West 27th Street, Minneapolis, MN 55408 (US).			
(74) Agent: MACKINNON, Ian, D.; Honeywell Inc., P.O. Box 524, Honeywell Plaza MN12-8251, Minneapolis, MN 55440-0524 (US).			

(54) Title: **POLYMER MICROACTUATOR ARRAY WITH MACROSCOPIC FORCE AND DISPLACEMENT**

(57) Abstract

A microactuator array device, which includes a plurality of generally parallel thin flexible polymer sheets bonded together in a predetermined pattern to form an array of unit cells on at least one layer. Thin conductive and dielectric films are deposited on the sheets to form a plurality of electrodes associated with the array of unit cells. A source of electric potential operably connects the electrodes, whereby electrostatic forces are generated most intensely proximate the point where the gap between the sheets is smallest. Inlets and outlets for each cell permit displacement of fluid during generation of the electrostatic forces. In a preferred embodiment, the plurality of sheets forms a stack of layers of arrays of unit cells. The layers are configured such that bi-directional activation is caused by pairs of actuators working opposite each other. At least one of every pair of the sheets may be preformed into corrugations or into flaps to provide a predetermined mechanical bias between the pairs, or the sheets may form curved portions by an applied load to provide a displacement between the pairs. The sheets are preferably from about 1 μm to about 100 μm thick and the cells preferably have an individual displacement of from about 5 μm to about 200 μm .



11

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**POLYMER MICROACTUATOR ARRAY
WITH MACROSCOPIC FORCE AND DISPLACEMENT**

FIELD OF THE INVENTION

The present invention relates to microactuators having macroscopic force and displacement. More particularly the invention relates to microactuators comprising a 3-D array of small actuator cells which are formed from plastic sheets provided with electrodes and stacked.

BACKGROUND OF THE INVENTION

Most microactuator arrays, used as MEMS devices, are fabricated in silicon. Despite the many favorable attributes of silicon, however, it is not always a suitable or ideal material for every application of MEMS. Silicon is brittle and subject to breaking, particularly as the total device size increases. This brittleness limits devices, especially actuators, to relatively small sizes capable of only small displacements and forces. The shapes that can be realized in silicon are typically restricted by crystalline planes or 2-D fabrication processes, and more complicated structures often result in prohibitively high cost and low yield.

It would be of great advantage to the art if another material, other than silicon, could be used for MEMS and actuators.

It would be another great advance in the art if the material would not be brittle and subject to breaking, thus not limiting the size and therefore the displacement and force of the final device. Other advantages will appear hereinafter.

SUMMARY OF THE INVENTION

It has now been discovered that the above and other advantages of the present invention may be realized in the following manner. Specifically, the present invention comprises a microactuator capable of macroscopic forces and displacements suitable for many "real world" applications.

The invention contemplates the formation of a 3-D array of small actuator cells, each of which is capable of a small force and small displacement. When coupled or ganged together, either in parallel, in series, or both, the resultant array is capable of generating macroscopic forces and displacements simultaneously.

In the present invention, position resolution is as small as the displacement of the smallest unit cell or cells in the array. Actuation is accomplished electrostatically, using the attraction at the smallest gap between electrodes to produce a "rolling" motion in the cells. The invention may be operated.

Key to the invention is the use of polymer materials rather than silicon, as silicon is not capable of being formed into the present device. A resulting lightweight, easily fabricated, low cost device is the result of the present invention.

5 The microactuator array device of this invention is formed from a plurality of generally parallel thin flexible polymer sheets bonded together in a predetermined pattern to form an array of unit cells on the various layers. Thin layers of conductive films and dielectric materials are deposited on the sheets to form a plurality of electrodes associated with the array of unit cells in a conventional manner.

Inlets and outlets are used during generation of electrostatic forces.

10 A source of electric potential operably connects the electrodes whereby adjacent layers of electrodes are biased with respect to each other to generate electrostatic action. Electrostatic actuation is a pull type action, so pairs of actuators work with each other to accomplish bi-directional activation.

15 BRIEF DESCRIPTION OF THE DRAWINGS

For a more complete understanding of the invention, reference is hereby made to the drawings, in which:

Figure 1 is a schematic view, partially cut away and in section, showing a first embodiment of the present invention;

20 Figure 2 is a schematic view, partially cut away and in section, showing a second, related embodiment of the present invention;

Figure 3 is a graphical illustration of force per unit cross section for three polymer sheet thicknesses.

25 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The present invention provides an improved, low power microactuator array having significantly greater macroscopic force and displacement than heretofore possible in silicon based MEMS devices. This is accomplished by the use of polymers as a class of materials for forming actuators of the type described herein. Polymers 30 possess a wide range of properties, most of them being complimentary to silicon. In the present invention environment, polymers are not brittle and do not break under the forces generated by the devices of this invention. For this reason, actuators are not limited to small sizes with small displacement and force.

35 The resulting arrays are fully 3-D in realization, due to the many fabrication techniques available now in polymer technology. Since polymers are lightweight, having a typical density in the range of 1g/cm^3 , essentially the same as water, they are considerably lighter than typical inorganic materials such as silicon. This gives the present invention a power to mass ration which compares favorably with other systems, such as, for example, biological systems.

The key features of the present invention and the application of polymer technology to fabrication of a family of MEMS actuators not possible heretofore with traditional silicon micromachining is the generation of large forces and displacements with actuation from low power electrostatic arrays that spatially separate the high force and high deflection regions. Force and displacement are multiplied by the use of a 3-D array of unit cells. Additionally, the uniformity and simplicity of the individual parts translates into a cost effective fabrication process, using many standard polymer processing techniques. These techniques may have to be refined to meet more demanding requirements of the present technology.

One embodiment of the present design is shown in Fig. 1, while a similar embodiment is illustrated in Fig. 2. Construction of both embodiments, as well as other forms of the present invention, begins with polymers formed into thin sheets. The sheets are preferably from about 1 μm to about 100 μm thick, and the cells preferably have an individual displacement of from about 5 μm to about 200 μm .

It is only required that the sheets be flexible and not brittle, properties found in many polymers. One particularly useful polymer is the polyimide sold as KAPTON® (registered trademark of E. I. du Pont de Nemours & Co., Wilmington, Delaware). Others include KALADDEX® (registered trademark of ICI Films, Wilmington, Delaware) and MYLAR® (registered trademark of E. I. du Pont de Nemours & Co., Wilmington, Delaware), or any flexibly elastic polymer that permits it to deform as described herein. Fabrication of the sheets may be based, in part, upon technology developed for keyboard and flexible circuits that are produced in huge quantities, making the process well optimized. Preferred sheets are made from polymer films such as KAPTON® or MYLAR® (registered trademark of E. I. du Pont de Nemours & Co., Wilmington, Delaware), or different polymers that are or become commercially available. The invention also contemplates the use of conductive polymers with a dielectric, thus eliminating the need for separate electrodes in this embodiment.

As seen in Figs. 1 and 2, a polymer-based microactuator array 11, generally, comprises a plurality of polymeric sheets 13. In Fig. 1, alternating sheets 15 are flat, although this is not necessary for the purposes of this invention, and alternating sheets 17 are corrugated. Having one flat sheet 15 results in larger forces, while corrugated sheets 17 are more flexible. In Fig. 2, alternating with flat sheets 15 are sheets 19 formed in parallel rows of flaps 21. In any form of the present invention, the sheets 13 may be preformed with a specific curvature, such as corrugations 17 or flaps 21, or left flat to be curved by the applied load during use, depending upon design considerations and the final use of the microactuator array being contemplated.

In all applications, the sheets 13 are bonded together at specific points 23, forming an array of unit cells 25 in Fig. 1 or cells 27 in Fig. 2. Each cell 25, or 27 or those formed by or under an applied load during use, produces a small force and small

displacement. The total force is the sum of the forces from all unit cells on the sheet. Sheets of unit cells are then stacked, such as 15a, 15b, etc. in Fig. 1. The total displacement is the sum of the displacements of each layer in the stack.

5 Layers in the stack may be actuated independently, resulting in positioning anywhere from zero to the maximum displacement, with resolution equal to the displacement of the smallest layer in the stack. The stack may be actuated individually, or in combinations of layers.

10 It is possible to construct a wide variety of arrays under the concepts of the present invention. For example, the cells shown in Fig. 1 are parallel rows of corrugations, whereas Fig. 2 illustrates parallel rows of flaps. A 2-D arrangement of corrugations, flaps and/or membranes is another example of the orientation of the polymeric sheets. Also, each cell in a given layer need not be the same dimension as the others. It is contemplated to make some corrugations, membranes or flaps smaller or differently shaped than others, to limit the total displacement from that layer.

15 Alternatively, cell dimensions may be varied within one layer so as to have the total displacement different on different parts of that layer. During operation of this embodiment, the curvature of the sheet would vary, resulting in an orientation change of the actuated load or the application of a bending moment to the load. For example, flat sheets are employed in a design similar to Fig. 1, the load would be applied on the hook

20 20 at the bottom of the device.

Of course, the displacement of each layer need not be the same as that of other layers. For example, a stack may be constructed from individual layers designed for displacements ranging from less than 5 μm to more than 200 μm . Total displacements, which are the sum of the individual layers, can easily exceed 1 mm using a modest

25 number of layers, with position accuracy of, say, 5 μm or the smallest layer used.

The polymeric layers 13 also include thin metal films 31 on the front and back surfaces of each sheet, to function as electrodes. Adjacent layers are biased with respect to each other, generating large electrostatic forces at the points where the gap 33

30 between sheets is small. The gap closes under these forces, beginning at the joints and "rolling" in toward the center of the cell. Although this sheets of plastic are very flexible, elastic force come into play when structure dimensions are a few millimeters or less.

The exact design and dimensions of the array can be varied, depending upon whether the goal is maximum output, as measured by force, displacement or work, or

35 maximum output per unit weight or volume. Fig. 3 illustrates some preliminary simulated results, not optimized, to demonstrate the force and displacement of an actuator design according to the present invention. A single unit cell 0.5 cm across and 1 cm along the corrugation, as depicted in Fig. 1, can generate a force of 1 N at under 60 volts. Fig. 3 also demonstrates that there is only a small penalty in force as the

maximum displacement is increased, further illustrating the broad range of use for the present invention.

As noted above, actuation of the present invention is accomplished electrostatically. Each layer is biased relative to the adjacent layers, so that strong electric fields (and forces) are present near the point where the layers are in contact, or where the gap 33 is small. These forces pull the sheets together. Since sufficient forces are generated only in the small gap regions, the force does not change significantly as a function of displacement. By nature, the electrostatic force between the sheets is attractive rather than repulsive. Thus the actuator pulls but does not push. Bi-directional actuation is achieved by using two actuators working opposite each other.

Position control in each layer can be achieved either by a two-state scheme where each layer is either fully extended or fully collapsed, or by a continuous scheme where intermediate positioning is possible by an appropriate choice of geometry and applied voltage.

The power source for the actuators of the present invention may be low voltage, such as with a battery although a voltage multiplier may be needed in that case. AC and DC actuator power supplies exist currently or have been designed for producing power for micropump and microvalve applications. Miniaturization of the present invention is contemplated for use with such power sources. Fig. 1 illustrates a power connector 37 and an appropriate control chip 39. In forming the final product using the present invention, one or more chips 39 may be embedded in the housing of the actuator as in Fig. 1. Contact is to the chips via a snap-on cap or flip chip, or other commonly used packaging technology. The dimensions and spacing of the bond pads on each part are designed such that no alignment would be needed beyond the snap-on alignment. The depth of the well for a chip is such that when the cap is snapped in place, sufficient pressure always exists to make a reliable electrical bond. If desired, plating with indium or gold can be used to achieve an even more reliable connection through cold welding. The housing of the actuator can contain one or more levels of metal interconnects, as in a printed circuit board, to route the input from the external connector through the control circuitry, and finally to the sheets of the actuator.

Contact is made from an inlet 41, shown in Fig. 2, to the individual sheets through flexible plastic lines as in a conventional flex-tape connector. The lines can be metalized plastic or conductive polymer, and, in fact, may be cut from the same polymer sheet as in the stack layers. Layers can be electrically tied together or can be individually addressed, depending on the degree of control and sophistication of the end use, noting that individual addressing requires more connections so it would involve higher cost but finer control when needed.

The present invention offers new ways of making MEMS not currently available to silicon-based MEMS fabrication. The actuator fabrication process has three main

steps: fabrication of the individual sheets; bonding the sheets in the desired configuration; and attachment of the actuator to a housing.

The individual sheets can be preformed using low cost processes such as cutting or stamping, rather than photolithography and etching. The structures may be defined as perforated lines rather than cutting them completely free. Then, once all the layers have been bonded together, the perforations can be broken, separating the layers, by pulling on the ends of the stack. Heat is effective in bonding the sheets together, as would be an adhesive, the latter being less preferred because of the increased spacing between layers with a resultant reduction in force.

Aluminum or other metal or alloy electrodes and one or more dielectric films, such as aluminum oxide or poly-para-xylene, or other suitable organic or inorganic dielectrics, are deposited on both sides of each sheet as described above. The conductive portion forms the electrode and the dielectric prevents shorting of the electrodes when they touch. These films can be patterned using standard patterning techniques, such as those to make printed circuit boards. The top dielectric layer should produce a chemically stable surface with a very low surface energy. This is also helpful in controlling stiction. The hydrophobic character of the final layer eliminates humidity effects which are the cause of most operational failures in touch-mode electrostatic actuators. The level of performance that can be obtained from an electrostatic actuator depends on the dielectric strength of the material used as a dielectric.

As will become apparent from the foregoing detailed description, the present invention is admirably suited for various applications, such as portable or airborne systems where weight is critical, or systems operated remotely over a low power bus line. Other operations such as remotely operated ground and water vehicles, robotics, positioning system shutters, valves and pumps are among the devices contemplated for this invention.

While particular embodiments of the present invention have been illustrated and described, it is not intended to limit the invention, except as defined by the following claims.

CLAIMS

1. A microactuator array device, comprising:
a plurality of generally parallel thin flexible polymer sheets bonded
together in a predetermined pattern to form an array of unit cells on at least one layer;
5 thin conductive and dielectric films deposited on said sheets to form a
plurality of electrodes associated with said array of unit cells;
a source of electric potential operably connecting said electrodes such
that adjacent layers of electrodes are biased with respect to each other to form actuators,
whereby electrostatic forces are generated most intensely proximate the point where the
10 gap between said sheets is smallest; and
inlets and outlets for each cell to permit displacement of fluid during
generation of said electrostatic forces.
2. The device of claim 1, wherein said plurality of sheets forms a stack of
15 layers at least one unit cell per layer.
3. The device of claim 2, wherein said layers are configured such that bi-
directional activation is caused by pairs of actuators working opposite each other.
- 20 4. The device of claim 1, wherein at least one of every pair of said sheets
are preformed into corrugations to provide a predetermined mechanical bias between
said pairs.
5. The device of claim 1, wherein at least one of every pair of said sheets
25 are preformed into flaps to provide a predetermined mechanical bias between said pairs.
6. The device of claim 1, wherein said sheets form curved portions by an
applied load to provide a displacement between said pairs.
- 30 7. The device of claim 1, wherein said sheets are from about 1 μm to about
100 μm thick and said cells have an individual displacement of from about 5 μm to
about 200 μm .
8. A microactuator array device, comprising:
35 a plurality of generally parallel thin flexible polymer sheets bonded
together in a predetermined pattern to form an array of unit cells on at least one layer;
thin conductive and dielectric film means deposited on said sheets to
form a plurality of electrode means associated with said array of unit cells;

electric potential means for providing a source of electric potential operably connecting said electrodes such that adjacent layers of electrodes are biased with respect to each other to form actuator means, whereby electrostatic forces are generated most intensely proximate the point where the gap between said sheets is smallest; and

transfer means for each cell to permit displacement of fluid during generation of said electrostatic forces by operation of said electric potential means.

9. The device of claim 8, wherein said array means are configured such that bi-directional activation is caused by pairs of actuator means working opposite each other.

10. The device of claim 8, wherein at least one of every pair of said sheets are preformed into corrugations to provide a predetermined mechanical bias between said pairs.

11. The device of claim 8, wherein at least one of every pair of said sheets are preformed into flaps to provide a predetermined mechanical bias between said pairs.

12. The device of claim 8, wherein said sheets form curved portions by an applied load to provide a displacement between pairs.

13. The device of claim 8, wherein said sheets are from about 1 μm to about 100 μm inches thick and said cells have an individual displacement of from about 5 μm to about 200 μm .

14. A method of forming a microactuator array device, comprising the steps of:

depositing thin conductive and dielectric films on said sheets to locate and pattern a plurality of electrodes associated with said array of unit cells;

operably connecting a source of electric potential to said electrodes such that adjacent layers of electrodes are biased with respect to each other to form actuators, whereby electrostatic forces are generated most intensely proximate the point where the gap between said sheets is smallest; and

bonding a plurality of generally parallel thin flexible polymer sheets together in a predetermined pattern to form an array of unit cells on at least one layer;

connecting inlets and outlets for each cell to permit displacement of fluid during generation of said electrostatic forces.

15. The method of claim 14, wherein said plurality of sheets are stacked to a stack of at least one unit cell per layer.
- 5 16. The method of claim 15, wherein said layers are configured such that bi-directional activation is caused by pairs of actuators working opposite each other.
- 10 17. The method of claim 14, wherein at least one of every pair of said sheets are preformed into corrugations to provide a predetermined mechanical bias between said pairs.
18. The method of claim 14, wherein at least one of every pair of said sheets are preformed into flaps to provide a predetermined mechanical bias between said pairs.
- 15 19. The method of claim 14, wherein said sheets form curved portions by an applied load to provide a predetermined bias between said pairs.
- 20 20. The method of claim 14, wherein said sheets are formed from about 1 μm to about 100 μm thick and said cells are formed to have an individual displacement of from about 5 μm to about 200 μm .

1/2

11




Fig.1





Fig. 3

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 H02N1/00		International Application No PCT/US 99/28066
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 H02N H01H		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	MOTOHARU YAMAGUCHI ET AL: "DISTRIBUTED ELECTROSTATIC MICRO ACTUATOR" PROCEEDINGS OF THE WORKSHOP ON MICRO ELECTRO MECHANICAL SYSTEMS (MEMS), US, NEW YORK, IEEE, vol. WORKSHOP 6, 1993, pages 18-23, XP000366849 ISBN: 0-7803-0957-X the whole document --- -/--	1-4, 6-10, 12-17, 19,20
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.		
<input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "A" document member of the same patent family		
Date of the actual completion of the international search 7 March 2000		Date of mailing of the international search report 14/03/2000
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 851 epo nl Fax: (+31-70) 340-3018		Authorized officer Ramirez Fueyo, M

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/28066

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	MINAMI K ET AL: "FABRICATION OF DISTRIBUTED ELECTROSTATIC MICRO ACTUATOR (DEMA)" JOURNAL OF MICROELECTROMECHANICAL SYSTEMS,US,IEEE INC. NEW YORK, vol. 2, no. 3, 1 September 1993 (1993-09-01), pages 121-127, XP000426532 ISSN: 1057-7157 the whole document	1
A	US 2 975 307 A (C.E.SCHROEDER) 14 March 1961 (1961-03-14) the whole document	1
A	WO 96 34701 A (UNIV BRITISH COLUMBIA) 7 November 1996 (1996-11-07) page 5, line 7 -page 6, line 5 page 12, line 35 -page 15, line 8 figures 3,4,5A,5B	5,11,18

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Application No
PCT/US 99/28066

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 2975307	A	14-03-1961	NONE	
WO 9634701	A	07-11-1996		
			US 5642015 A	24-06-1997
			AU 5394596 A	21-11-1996
			CA 2218876 A	07-11-1996
			CN 1186458 A	01-07-1998
			EP 0824381 A	25-02-1998
			JP 10511528 T	04-11-1998